



UNITED ALLOY # 310

Thank you for using UNITED'S alloys.

UNITED'S 310 ALLOY may be used for 10K - 18K casting, which produces a greenish finished color in 10K & 14K, and a rich yellow finished color in 18K, and is zinc free.

You should obtain excellent results by following a few simple instructions.

MELTING

Melt Temperature for 10 & 14K Alloyed Grain 980° - 990° C.
1796° - 1814° F.

Melt Temperature for 18K Alloyed Grain 1010° C / 1850° F.

Melt Temperature for Alloying 1030° - 1050° C.
1886° - 1922° F.

We do recommend pre-graining all alloy and fine gold before casting to assure a uniform mixture.

FLASK TEMPERATURE

Normal recommended temperature.

FLUXING

Boric Acid is the recommended flux. Use as little flux as possible. Do not use carbon fluxes or any fluxes designed for refining; i.e., soda ash, saltpeter, etc. Avoid flux in bottom pour automatic casting units.

QUENCH TIME

15 – 20 minutes.

INVESTMENT REMOVAL

Most standard investment removers will successfully remove the investment powder. Fluoric-based investment removers are the best for removing the silicon oxide invisible coating. UNITED'S Brite-Cast Investment Remover also works very well.

REMELTING

We recommend a 50% rejuvenation for remelting.

NOTES

Melt temperature may vary with type of unit. This alloy is designed for casting only.

TECHNICAL ASSISTANCE

Always available...

Call 1-800-999-3463 / 1-800-999-FINE.

E-mail / doc@unitedpmr.com

Web-Site / <http://www.unitedpmr.com/>

2781 Townline Road, Alden, NY 14004

Phone: 1 (800) 999-FINE (3463) Intl. Phone: + 1 (716) 683-8334

Fax: 1 (800) 533-6657 Intl. Fax: +1 (716) 683-5433

E mail: sales@unitedpmr.com Website: www.unitedpmr.com