



UNITED ALLOY # 575

Thank you for using UNITED'S alloys.

UNITED'S 575 ALLOY may be used for 10K - 18K casting, and hand-made (rolling), which produces a green finished color.

You should obtain excellent results by following a few simple instructions.

MELTING

Melt Temperature for 10 & 14K Alloyed Grain 970° - 980° C.
1778° - 1796° F.

Melt Temperature for 18K Alloyed Grain 1030° - 1040° C.
1886° - 1904° F.

Melt Temperature for Alloying 1040° - 1050° C.
1904° - 1922° F.

We do recommend pre-graining all alloy and fine gold before casting to assure a uniform mixture.

FLASK TEMPERATURE

Normal recommended temperature.

FLUXING

Boric Acid is the recommended flux. Use as little flux as possible. Do not use carbon fluxes or any fluxes designed for refining; i.e., soda ash, saltpeter, etc. Avoid flux in bottom pour automatic casting units.

QUENCH TIME

8 – 12 minutes. Casting for hand-made, quench ingot immediately.

INVESTMENT REMOVAL

Most standard investment removers will successfully remove the investment powder. Fluoric-based investment removers are the best for removing the silicon oxide invisible coating. UNITED'S Brite-Cast Investment Remover also works very well.

REMELTING

We recommend 50% rejuvenation for remelting.

NOTES

Melt temperature may vary with type of unit. This alloy is designed for casting and hand-made (rolling).

TECHNICAL ASSISTANCE

Always available...
Call 1-800-999-3463 / 1-800-999-FINE.
E-mail / doc@unitedpmr.com
Web-Site / www.unitedpmr.com

2781 Townline Road, Alden, NY 14004
Phone: 1 (800) 999-FINE (3463) Intl. Phone: +1 (716) 683-8334
Fax: 1 (800) 533-6657 Intl. Fax: +1 (716) 683-5433
E mail: sales@unitedpmr.com Website: www.unitedpmr.com

2781 Townline Road, Alden, NY 14004
Phone: 1 (800) 999-FINE (3463) Intl. Phone: + 1 (716) 683-8334
Fax: 1 (800) 533-6657 Intl. Fax: +1 (716) 683-5433
E mail: sales@unitedpmr.com Website: www.unitedpmr.com