



### UNITED ALLOY # 782

Thank you for using UNITED'S alloys.

UNITED'S 782 ALLOY is designed for 18K yellow gold casting, which produces a light yellow color.

You should obtain excellent results by following a few simple instructions.

#### **MELTING**

Melt Temperature for 18K Alloyed Grain      1010° - 1020° C.  
1850° - 1868° F.

Melt Temperature for Alloying                      1050° - 1070° C.  
1922° - 1958° F.

We do recommend pre-graining all alloy and fine gold before casting to assure a uniform mixture.

#### **FLASK TEMPERATURE**

We recommend a slightly higher flask temperature for 18K.

#### **FLUXING**

Boric Acid is the recommended flux. Use as little flux as possible. Do not use carbon fluxes or any fluxes designed for refining; i.e., soda ash, saltpeter, etc. Avoid flux in bottom pour automatic casting units.

#### **QUENCH TIME**

15 – 20 minutes.

#### **INVESTMENT REMOVAL**

Most standard investment removers will successfully remove the investment powder. Fluoric-based investment removers are the best for removing the silicon oxide invisible coating. UNITED'S Brite-Cast Investment Remover also works very well.

#### **RE MELTING**

We recommend 50% rejuvenation for remelting.

#### **NOTES**

Melt temperature may vary with type of unit. This alloy is designed for casting only.

#### **TECHNICAL ASSISTANCE**

Always available...  
Call 1-800-999-3463 / 1-800-999-FINE.  
E-mail / [doc@unitedpmr.com](mailto:doc@unitedpmr.com)  
Web-Site / <http://www.unitedpmr.com/>

**2781 Townline Road, Alden, NY 14004**

Phone: 1 (800) 999-FINE (3463) Intl. Phone: + 1 (716) 683-8334

Fax: 1 (800) 533-6657 Intl. Fax: +1 (716) 683-5433

E mail: [sales@unitedpmr.com](mailto:sales@unitedpmr.com) Website: [www.unitedpmr.com](http://www.unitedpmr.com)