



UNITED ALLOY # 906

Thank you for using UNITED'S alloys.

UNITED'S 906 ALLOY may be used for 10K & 14K white gold casting, which produces a white finished color. #906 has high fluidity and contains small amounts of silicon & boron deoxidizers. This alloy has a good white color and has been proven to perform very well for Stone-In-Place castings.

You should obtain excellent results by following a few simple instructions.

MELTING

Melt Temperature for 10K Alloyed Grain	1040° - 1055° C. 1904° - 1931° F.
Melt Temperature for 14K Alloyed Grain	1035° - 1050° C. 1895° - 1922° F.
Melt Temperature for Alloying	1050° - 1060° C. 1922° - 1940° F.

We do recommend pre-graining all alloy and fine gold before casting to assure a uniform mixture.

FLASK TEMPERATURE

We suggest a slightly higher flask temperature for white gold in the range of 1050 F to 1250 F depending on the size of flask and type of jewelry styles.

FLUXING

Fluxing white gold is extremely important to pick-up oxides. Boric Acid is the recommended flux. Do not use carbon fluxes or any fluxes designed for refining; i.e., soda ash, saltpeter, etc. Avoid flux in bottom pour automatic casting units.

QUENCH TIME

15 to 20 minutes after pouring. Quench button first for 30 sec.

INVESTMENT REMOVAL

Most standard investment removers will successfully remove the investment powder. Fluoric or Phosphoric acid-based investment removers are the best for removing the silicon oxide invisible coating. UNITED'S Brite-Cast Investment Remover also works very well.

REMELTING

We recommend a 70% fresh - 30% scrap mix.

NOTES

Melt temperature may vary with type of unit. This alloy is designed for casting only.

TECHNICAL ASSISTANCE

Always available...
Call 1-800-999-3463 / 1-800-999-FINE.
E-mail / doc@unitedpmr.com
Web-Site / www.unitedpmr.com

2781 Townline Road, Alden, NY 14004

Phone: 1 (800) 999-FINE (3463) Intl. Phone: + 1 (716) 683-8334

Fax: 1 (800) 533-6657 Intl. Fax: +1 (716) 683-5433

E mail: sales@unitedpmr.com Website: www.unitedpmr.com