

Technical sheet - Alloy 315

Color - Bright yellow

Purpose - All purpose

Karat - 18K

Physical & Mechanical Properties

Composition		Color Coordinates				Density (g/cc)		As cast Hardness (HV)	
		Karat	L*	a*	b*				
Cu	41.75%	18K 315	89.44	3.27	25.48	18K 315	15.36	18K 315	146
Ag	57.25%								
Zn	1.00%								
Ni	0.00%								

Melting & Casting Instructions

Temperatures			
	Karat	°C	°F
Pre alloying	18K	1030° C - 1050° C	1886° F - 1922° F
Casting	18K	975° C - 995° C	1787° F - 1823° F
Flask	18K	510° C - 650° C	950° F - 1202° F

Quench Time	15-20 Minutes
-------------	---------------

Remelting	50% Fresh Mix
-----------	---------------

General Instructions

- Very little *boric acid* flux is recommended. Do not use carbon flux such as soda ash, saltpeter etc. No flux needed in bottom pour automatic casting unit.
- *Flouric based* investment removers are the best for silicon oxide invisible coating. Use of aggressive acid causes corrosion and surface damage. *United's brite cast* investment removers works effectively.
- To calculate the weight of the metal needed (in grams), *multiply density (gm/cc) with weight of wax (grams)*. Add 10% of the total weight for button.
- *Gypsum bonded* investment is recommended. Follow manufacturer's instruction for burnout cycle.

Note: There are proprietary metals in the formulation which are not included in the composition section.

Technical Assistance: Always available... Call 1-800-999-3463 / 1-800-999-FINE

E-mail / techteam@unitedpmr.com Web-Site / www.unitedpmr.com